



		VDI 3323	Vc [m/min]
P	Unalloyed steel, leaded steel	1 - 5	30
	Low alloyed steel < 800 N/mm <sup>2</sup>	6 - 9	25
	High-alloy steel > 800 N/mm <sup>2</sup> , stainless steel ferr.- marten.	10 - 13	20
M	Austenitic stainless steel < 700 N/mm <sup>2</sup>	14.1-14.2	25
	Nickel-free stainless steel/DUPLEX >700 N/mm <sup>2</sup>	14.3-14.4	20
K	Grey cast iron < 250 HB	15 - 16	30
	Ductile, malleable, nodular cast iron > 250 HB	17 - 20	25
N	Wrought aluminium alloy < 12% Si	21 - 22	50
	Cast aluminium alloy >12% Si	23 - 25	40
	Copper alloy good machinability with Pb	26	40
	Copper alloy with difficult machinability	27 - 28	40
	Plastics, wood	29 - 30	40
	Gold, silver	-	30
S	Refractory alloy, Fe, Ni, Co base	31- 35	10
	Titanium, titanium alloy	36 - 37	15



$$n \text{ [rpm]} = \frac{Vc \text{ [m/min]} \times 1000}{\pi \times D_1 \text{ [mm]}}$$

$$Vf \text{ [mm/min]} = n \text{ [rpm]} \times f \text{ [mm]}$$

Feed per revolution f [mm]													
Ø D <sub>1</sub> 0.40 - 0.80		Ø D <sub>1</sub> 0.80 - 1.20		Ø D <sub>1</sub> 1.20 - 2.50		Ø D <sub>1</sub> 2.50 - 4.20		Ø D <sub>1</sub> 4.20 - 6.20		Ø D <sub>1</sub> 6.20 - 8.00		Ø D <sub>1</sub> 8.00 - 12.00	
f (rpm)	Ream-all. (mm)	f (rpm)	Ream-all. (mm)	f (rpm)	Ream-all. (mm)	f (rpm)	Ream-all. (mm)	f (rpm)	Ream-all. (mm)	f (rpm)	Ream-all. (mm)	f (rpm)	Ream-all. (mm)
0.02-0.03	0.05	0.03-0.04	0.05	0.05-0.06	0.05	0.08-0.10	0.1	0.15-0.20	0.1	0.18-0.25	0.2	0.25-0.30	0.2
0.02-0.03	0.05	0.03-0.04	0.05	0.05-0.06	0.05	0.08-0.10	0.1	0.15-0.20	0.1	0.18-0.25	0.2	0.25-0.30	0.2
0.01-0.02	0.05	0.02-0.03	0.05	0.04-0.05	0.05	0.08-0.10	0.1	0.08-0.10	0.1	0.08-0.10	0.2	0.08-0.10	0.2
0.02-0.03	0.05	0.03-0.04	0.05	0.05-0.06	0.05	0.08-0.10	0.1	0.15-0.20	0.1	0.18-0.25	0.2	0.18-0.25	0.2
0.02-0.03	0.05	0.03-0.04	0.05	0.05-0.06	0.05	0.08-0.10	0.1	0.15-0.20	0.1	0.15-0.20	0.2	0.15-0.20	0.2
0.02-0.03	0.05	0.03-0.04	0.05	0.05-0.06	0.05	0.08-0.10	0.1	0.15-0.20	0.1	0.18-0.25	0.2	0.25-0.30	0.2
0.02-0.03	0.05	0.03-0.04	0.05	0.05-0.06	0.05	0.08-0.10	0.1	0.15-0.20	0.1	0.18-0.25	0.2	0.25-0.30	0.2
0.03-0.04	0.05	0.04-0.06	0.05	0.06-0.08	0.1	0.10-0.15	0.1	0.20-0.25	0.1	0.25-0.30	0.2	0.30-0.40	0.2
0.03-0.04	0.05	0.04-0.06	0.05	0.06-0.08	0.1	0.10-0.15	0.1	0.20-0.25	0.1	0.25-0.30	0.2	0.30-0.40	0.2
0.03-0.04	0.05	0.04-0.06	0.05	0.06-0.08	0.1	0.10-0.15	0.1	0.20-0.25	0.1	0.25-0.30	0.2	0.30-0.40	0.2
0.03-0.04	0.05	0.04-0.06	0.05	0.06-0.08	0.1	0.10-0.15	0.1	0.20-0.25	0.15	0.25-0.30	0.2	0.30-0.40	0.2
0.03-0.04	0.05	0.04-0.06	0.05	0.06-0.08	0.1	0.10-0.15	0.1	0.20-0.25	0.1	0.25-0.30	0.2	0.30-0.40	0.2
0.02-0.03	0.05	0.03-0.04	0.05	0.05-0.06	0.05	0.08-0.10	0.05	0.08-0.10	0.1	0.10-0.12	0.1	0.12-0.015	0.15
0.02-0.03	0.05	0.03-0.04	0.05	0.05-0.06	0.05	0.08-0.10	0.05	0.08-0.10	0.1	0.10-0.12	0.1	0.12-0.15	0.15

Values based on use of cutting oil. The cutting parameters are very strongly influenced by external parameters, such as tool and workpiece stability, etc. The cutting conditions must be adapted to the operating conditions !